

best wood **TOP 140**

Version 01/2022



Technical information

Denomination	WF-EN 13171-T5-DS(70,-)2-CS(10\Y)100-TR20-WS1,0-MU3-AFr75
Norm	EN13171
Density	140 [kg/m ³]
Nominal value of thermal conductivity λ_D	0.040 [W/(mK)]
Rated value of thermal conductivity λ	0.042 [W/(mK)]
Reaction to fire according to DIN EN 13501	E
Construction material class according to DIN 4102	B2
Full declaration	Wood fibers, PMDI gluing, paraffin, Latex
Production process	Dry process
Compressive stress at 10% compression	≥ 100 [kPa]
Tensile strength perpendicular to the plane of the board	≥ 20 [kPa]
Modulus of elasticity $E_{(d)}$	≥ 1.45 [N/mm ²]
Water vapor diffusion resistance μ	3
Linear flow resistance	> 75 [kPa·s/m ²]
Short time water absorption	< 1.0 [kg/m ²]
Specific heat capacity	2,100 [J/(kg K)]
Waste code according to AVV	030105, 170201

Delivery formats (standard formats)

Edge formats	Tongue + groove
Thickness	80,100, 120, 140, 160, 180, 200, 220, 240 mm
Length	2,000 mm
Width	580 mm
Pallet height	up to a max. of 1,350 mm

Other board lengths are possible on request.

TOP 140 is a pressure-resistant, weatherproof insulation board and a rain-proof sarking board, classified as ZVDH class 3 (ZVDH = Federation of German Roofing Contractors). Furthermore, TOP is also ideally suitable for weatherproof facade insulation on both-closed and ventilated curtain wall facades. Due to the use of paraffin (wax), the best wood board is completely water-repellent. The surface is equipped with an anti-slip latex coating. TOP 140 is weatherproof for up to 12 weeks' outdoor exposure. The application of nail sealing tapes is not necessary.

Fields of application according to DIN 4108-10

DAD-ds, DAA-ds, DEO-ds, WAB-ds, WZ, WH

DAD Outside insulation of roof or ceiling, protected against direct exposure to the weather, insulation under coverage

ds High pressure resistance

DAA Outside insulation of roof or ceiling, protected against direct exposure to the weather, insulation under coverage

DEO Inside insulation of the ceiling (on the top) under screed without noise protection requirements

WAB External insulation of the wall behind the cladding

WH Infilling insulation of walls in wooden framework and timber frame constructions


WZ Insulation of cavity walls, cavity insulation



Board weights

Thickness in mm	1 m ²	580 x 2,000 mm 1.16 m ²
80	11.2 kg	13.0 kg
100	14.0 kg	16.2 kg
120	16.8 kg	19.5 kg
140	19.6 kg	22.7 kg
160	22.4 kg	26.0 kg
180	25.2 kg	29.2 kg
200	28.0 kg	32.4 kg
220	30.8 kg	35.7 kg
240	33.6 kg	38.9 kg

Certificats



Installation advice

Die TOP 140 TOP 140 is to be laid on pressure and joint free. Even the smallest joints have to be closed with best wood FDM TOP before installing the counter batten.

- Store and install TOP 140 dry
- The tongue faces roof ridge, cross joints are not allowed
- Do not use TOP 180 statically or as load-bearing component
- Do not install damaged boards!
- Boards can only be walked on via the rafters
- Each TOP board has to cover at least two rafters. The joint displacement per row has to be at least 1 rafter space.
- Afterwards it has to be fixed immediately with the counter-batten.
- The boards have to be installed rectangularly to the rafter
- Connections on the roof ridge, covings, hips and penetrations have to

be sealed with the suitable system components

- Dust extraction in accordance with BG regulations
- Installation elements or inlets (e.g. solar pipes ...), for which temperatures of > 80°C can be expected, must not be installed without any additional fire precautions into the best wood SCHNEIDER wood fiber insulation materials.

Please note the special processing guidelines for ON-ROOF INSULATION.

When installing the TOP 140/160/180/220 directly onto the rafters, the following maximum rafter distances must be observed:

best wood on-roof insulation		TOP 140	TOP 160	TOP 180	TOP 220
maximum rafter distance [mm]	minimum board length [mm]	Thickness of board of the on-roof insulation [mm]			
≤ 750	2,000	≥ 80	≥ 60	≥ 35	≥ 22
≤ 850	2,000	≥ 100	≥ 80	≥ 50	≥ 35
≤ 1,100	2,500	≥ 140*	≥ 120*	≥ 80	≥ 50
≤ 1,250	2,500	≥ 200*	≥ 160*	≥ 100*	X

* Order-based production.

■ ■ ATTENTION!

All TOP boards are only treadable on the rafters. So boards can only be walked on via the rafters.

Fastening instructions

You have the possibility to calculate the screws required for fastening the on-roof insulation by yourself, using the free Heco software program. Alternatively, you can complete the fax information form and let Heco calculate the screws.

Furthermore, you can receive a calculation from ITW for ring nails, nail screws or clips by using the questionnaire fax. Please note that the calculation of ITW is only valid for ITW fixing elements. Remarks and boundary conditions in the result printout have to be considered.

The **cross-section of the counter-batten** is analyzed or stated depending on the fastening material when HECO and ITW do the calculation. Corresponding input forms can be found in the website www.schneider-holz.com.

No need for nail sealing tapes

As per rules and standards of the ZVDH, all TOP products are certified in the UDP-A class. In effectiveness of the examinations of the Holzforschung Austria it can be evidenced, that for connections of the counter-batten by means of screws, cleats, self-piercing screws or threaded nails, due to natural swelling behaviour, an application of nail sealing tapes is not necessary.

Das vorliegende technische Datenblatt entspricht dem derzeitigen Entwicklungsstand und verliert bei Erscheinen einer Neuauflage seine Gültigkeit. Vorschriften des jeweils gültigen Baurechts sind einzuhalten. Die vorliegenden Tabellen enthalten lediglich Richtvaluee. Technische Änderungen, Irrtümer und Druckfehler vorbehalten. Die Eignung und Angaben des Produktes sind in jedem Fall für den beabsichtigten Verwendungszweck bauseitig zu überprüfen. Eine Haftung durch best wood SCHNEIDER® GmbH ist ausgeschlossen.

